

Scheuten insulating laminated security glass


Isolide® Safe



Certified bulletproof glazing

Insulating double glazing

Test reports obtained in accordance with EN 1063

Class EN 1063	Type	Thickness (mm)	Weight (kg/m ²)	Test report	Other classifications
BR1-S	Isolide BR1-S.27.36.112	27	36	DSC-B 02 058	 <p>Ballistic test Bulletproof glass undergoes a ballistic test using various weapons and various types of ammunition. This ballistic test is based on NEN-EN 1063.</p>
	Isolide BR1-S.28.40.112	28	40	DSC-B 02 059	
BR1-NS	Isolide BR1-NS.34.51.112	34	51	DSC-B 02 061	
	Isolide BR1-NS.33.51.112	33	51	DSC-B 02 060	
BR2-S	Isolide BR2-S.38.61.112	38	61	DSC-B 02 063	
	Isolide BR2-S.37.58.112	37	58	DSC-B 02 062	
BR2-NS	Isolide BR2-NS.44.76.112	44	76	DSC-B 02 064	
BR3-S	Isolide BR3-S.39.62.112	39	62	DSC-B 02 066	
	Isolide BR3-NS.50.92.112	50	92	DSC-B 02 067	
BR4-S	Isolide BR4-S.42.67.112	42	67	DSC-B 02 069	
	Isolide BR4-S.46.81.112	46	81	DSC-B 02 068	
BR4-NS	Isolide BR4-NS.56.107.112	56	107	DSC-B 02 070	SG1-NS
BR5-S	Isolide BR5-S.54.102.112	54	102	DSC-B 02 071	
	Isolide BR5-S.52.97.112	52	97	S 03 0016 05/Z	
BR5-NS	Isolide BR5-NS.67.133.112	67	133	S 03 0016 04/Z	
BR6-S	Isolide BR6-S.63.123.112	63	123	DSC-B 02 072	
	Isolide BR6-S.69.134.112	69	134	DSC-B 02 073	
BR6-NS	Isolide BR6-NS.75.153.112	75	153	DSC-B 02 074	
BR7-S	Isolide BR7-S.84.173.112	84	173	S 03 0016 06/Z	
	Isolide BR7-S.86.178.112	86	178	S 03 0016 07/Z	
BR-7NS	Isolide BR7-NS.89.178.115	89	178	S 03 0053 01/Z	
SG1-S	Isolide SG1-S.46.81.112	46	81	S 03 0016 08/Z	
SG1-NS	Isolide SG1-NS.56.107.112	56	107	DSC-B 02 057	BR4-NS
SG2-S	Isolide SG2-S.62.122.112	62	122	DSC-B 02 056	
SG2-NS	Isolide SG2-S.81.168.112	81	168	DSC-B 02 055	

S Splinters released on secure side

NS No splinters released on secure side

Please refer to our website www.scheuten.com for the most recent information

